

POLYMERS

SABIC[®] LLDPE

R50035 Series

Linear Low Density Polyethylene for Rotational Molding & Compounding

PRODUCT DESCRIPTION:

SABIC[®] LLDPE R50035 series are Linear Low Density Polyethylene grades with balanced density and viscosity designed to provide excellent stress crack resistance, good mechanical properties with high rigidity and toughness with low warpage.

SABIC[®] LLDPE R50035 Series includes the following grades:

- R50035 : Non-UV stabilized in pellet form
- R50035E : AO and UV stabilized in pellet form
- RG50035: Non-UV stabilized reactor powder grade

TYPICAL APPLICATIONS:

Rotational molding of water tanks, industrial and agricultural tanks and containers, general purpose rotomolding articles where easy processing is required. RG50035 is typically suitable as carrier resin for producing compounds and masterbatches.

TYPICAL PROPERTY VALUES:

PROPERTIES	Unit	Value ⁽¹⁾	ASTM Method
Resin Properties			
Melt Flow Rate @ 190°C & 2.16 kg load	g/10 min.	5	D 1238
Density @ 23°C	kg/m ³	935	D 1505
MECHANICAL PROPERTIES ⁽²⁾			
Tensile Strength @ Yield	MPa	16	D 638
Tensile Strength @ Break	MPa	17	D 638
Tensile Elongation @ Break	%	590	D 638
1% Secant Modulus	MPa	420	D 790
Flexural Strength	MPa	13	D 790
Hardness (Shore D)	-	66	D 2240
ESCR (100% Igepal), F ₅₀	hrs	>150	D 1693B
THERMAL PROPERTIES			
Vicat Softening Point	°C	114	D 1525
Brittleness Temperature	°C	< -75	D 746

(1) Typical values; not to be construed as specification limits

(2) Based on injection molded specimens

PROCESSING CONDITIONS

Typical processing conditions for SABIC[®] LLDPE R50035 and R50035E are:

Oven temperature : 315°C (600°F)

Molding cycles vary with mold composition and its thickness, oven temperature and wall thickness of part being produced. Venting of the mold is recommended.

Processing temperature for extrusion machines for compounding : 200-240°C

FOOD REGULATION

SABIC® LLDPE R50035 Series resins are suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O. Box 5101, Riyadh 11422, Kingdom of Saudi Arabia
Tel: 966 1 2258000
Fax: 966 1 2259000

Technical Marketing
Tel: 966 1 2659166
Fax: 966 1 2653544

PE Sales:
Fax: 966 1 2258760
Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.